

⑫ 公開特許公報(A)

昭63-164858

⑮ Int.Cl.⁴
A 23 L 1/04識別記号 庁内整理番号
6760-4B

⑬ 公開 昭和63年(1988)7月8日

審査請求 有 発明の数 1 (全3頁)

⑭ 発明の名称 軟カプセルの外皮

⑯ 特 願 昭61-309109

⑰ 出 願 昭61(1986)12月27日

⑱ 発 明 者 久 保 寺 正 夫 神奈川県横浜市金沢区柴町203
⑲ 出 願 人 ユニコロイド株式会社 神奈川県逗子市桜山1丁目7番8号
⑳ 代 理 人 弁理士 鈴木 定子

明 細 書

1. 発明の名称

軟カプセルの外皮

2. 特許請求の範囲

多価アルコール、糖アルコール、単糖類、二糖類及びオリゴ糖から選ばれた少なくとも1種の濃厚溶液の中で、カラギナン、アルギン酸、アルギン酸誘導体、寒天、ローカストビーンガム、グァーガム、クマリンド種子多糖類、ペクチン、キサンタンガム、グルコマンナン、キチン質、プルラン、サイクロデキストリンから選ばれた少なくとも1種の天然多糖類を、アルカリの存在下或いは非存在下に、均一に混練して得られた天然多糖類・多価アルコール組成物を原料とする軟カプセルの外皮。

3. 発明の詳細な説明

(産業上の利用分野)

本発明は、油性以外の物質であっても充填することができる軟カプセルの外皮に関する。

(従来の技術)

軟カプセルはゼラチンを主体とするシートに油性の薬品等を充填したものであって、内容物の含有量が正確であること、接着面が完全密封されているため液漏れがなく内容物が外気と遮断され、酸化防止及び安定保存が図れ、しかも生産性が高い等の長所がある。

従来から軟カプセルはゼラチンを主原料とし、ゼラチンとグリセリンやソルビトール等を混合し、水溶液としたものをゲル化させシート状とし、このシート2枚を左右一対のダイロールから加熱しながらそれぞれ供給し、2枚のシート間に内容物を連続的に充填、密封後、乾燥して製造されている。

(発明が解決しようとする問題点)

軟カプセルは上記の通り、内容物の保存性、高生産性等の点で非常に優れているが、ゼラチンが水に溶解するため、内容物が水溶液の場合は利用できず、被充填薬品は油性溶媒に溶解しうるものに限られ、その利用範囲が制限されていた。そこで、水溶液の状態であっても軟カプセル状に充填

できる外皮が求められていた。

(問題解決の手段)

本発明は上記問題を解決するものであって、その構成は、軟カプセル外皮の原料として、多価アルコール、糖アルコール、単糖類、二糖類及びオリゴ糖から選ばれた少なくとも1種の濃厚溶液の中で、カラギナン、アルギン酸、アルギン酸誘導体、寒天、ローカストビーンガム、グァーガム、タマリンド種子多糖類、ペクチン、キサンタンガム、グルコマンナン、キチン質、プルラン、サイクロデキストリンから選ばれた少なくとも1種の天然多糖類と、場合によってはアルカリ及び/又は蛋白質の存在下に、均一に混練して得られた天然多糖類・多価アルコール組成物を用いることを特徴とする。

本発明に係る多価アルコールとしては、プロピレングリコール、グリセリン等の狭義の多価アルコールが挙げられる。糖アルコールとしては、ソルビトール、マンニトール、マルチトール、キシリトール、還元澱粉糖化物等が挙げられる。単糖

ンモニウム塩基性アミノ酸、アミン等が挙げられる。アルカリを添加すると一般にシートの強度、耐熱性が向上する。

更に、上記天然多糖類に蛋白質を併用することもできる。蛋白質としては大豆蛋白、小麦蛋白、ミルク蛋白、卵白、コラーゲン、コラーゲン分解物、微生物蛋白等が挙げられる。蛋白分解産物としては、ポリペプチド、ジペプチド、トリペプチド、アミノ酸が挙げられる。一般に、天然多糖類の一部に代えて蛋白質を併用して得られる組成物は強度が向上する傾向がある。

本発明は、これら多価アルコール、糖アルコール、単糖類、二糖類及びオリゴ糖から選ばれた少なくとも1種の濃厚溶液の中で天然多糖類が反応することに特徴がある。濃厚溶液とは、それ自体液状のものはそのまま、或いはわずかに希釈して使用し、粉体のものは30~90%水溶液、好ましくは50~80%、より好ましくは60~80%水溶液として、この中に上記多糖類の少なくとも1種を混練していく。

類としてはグルコース、フラクトース、ガラクトース、キシロース等が使用される。二糖類としてはサッカロース、マルトース、ラクトース等が使用される。オリゴ糖としてはさつま芋、じゃが芋、とうもろこし等の澱粉の酵素、酸などによる分解産物が使用され、二糖類、三糖類、四糖類、五糖類、六糖類等が含まれている。

天然多糖類とは、カラギナン、アルギン酸、アルギン酸誘導体、寒天、ローカストビーンガム、グァーガム、タマリンド種子多糖類、ペクチン、キサンタンガム、グルコマンナン、ムコ多糖類の一種であるキチン質、プルラン、サイクロデキストリン等も広く使用できる。

場合によっては、アルカリを併用することが好ましい。アルカリは通常の無機、有機のアルカリ性物質であればよく、例えば水酸化ナトリウム、水酸化カリウム、水酸化カルシウム、水酸化マグネシウム、水酸化バリウム、炭酸ナトリウム、炭酸カリウム、炭酸カルシウム、炭酸アンモニウム、炭酸マグネシウム、重炭酸ナトリウム、重炭酸ア

混練する温度は5~150℃で、好ましくは10~100℃で、より好ましくは20~80℃であり、低温で混練しても、後に乾燥する際などに加熱すれば十分に反応する。一般に、温度が高いと緻密な構造の組成物が得られ、温度が低いと網目構造が粗く脆い組成物が得られる。

天然多糖類と多価アルコール、糖アルコール、単糖類、二糖類及びオリゴ糖から選ばれた少なくとも1種の化合物との配合比は、天然多糖類1重量部に対し、これら化合物0.05~15重量部、好ましくは0.1~10重量部である。

上記原料を混練して得られた組成物は、一般に多少湿り気のある粉体である。これを水に溶解すると固形分2~10%の粘稠な溶液或いはペースト状となり、常温放置、凍結、冷蔵または加熱により不可逆的に凝固させることができる。しかも得られた凝固体は使用原料の組合せにより任意の物性、特に強度、耐熱性、水に対する溶解温度を調整することができるため、軟カプセルの外皮として好ましい。

本発明に係る軟カプセル外皮の態様としては、
 (A) ゼラチンシートに代えて本発明に係る組成物の水溶液を一旦、5～500 μ 好ましくは10～50 μ のシートに成形したシートを使用するもの、
 (B) ゼラチンシートと本発明に係る組成物のシートとを積層し、本発明に係るシートを内層にしたもの、
 (C) 軟カプセル用ゼラチン溶液と本発明に係る組成物溶液とを混合して乾燥したシートからなるもの、等が挙げられる。

軟カプセルの被充填物としては従来油性溶液として使用し難かった、ビタミンB₁、B₂、B₆、B₁₂、ナイアシン、葉酸、ビタミンC等の水溶性ビタミン、糖質、蛋白質、ミネラル等の栄養素、カプセル化した調味料や香辛料、一回の使用量ずつ小分けされた化粧料等が挙げられる。

(作用)

天然多糖類は種々の反応基や側鎖を有する複雑な構造であるため、多数の水酸基が高濃度に存在する濃厚溶液の中で反応し、複雑なマトリックス

を形成するものと考えられる。ここに水を加えることにより複雑な三次元構造が一層発達し、不可逆的に耐水性、耐熱性凝固体を形成するに至り、独特なゲル状物が形成される。

このようなゲル状物は耐水性であるため、水溶液の状態の薬剤、食品、化粧料などの被充填物を封入保存するための軟カプセル外皮として好ましく使用できる。

(実施例1)

ゼラチン100部、グリセリン30部、水60部を75℃で攪拌溶解し、真空ポンプで脱泡した。ロータリー式連続ソフトカプセル自動充填機にて厚さ450 μ のゼラチンフィルムとした。

別に、グルコマンナン5重量部、カラギナン2重量部、キサンタンガム1重量部を80%のサッカロース溶液1.5重量部と80℃で10分間混練して得た組成物3重量部を水97重量部に溶解した水溶液を湿式キャスト法で製膜し、厚さ25 μ のフィルムを得た。このフィルムに上記のゼラチンフィルムを重ねた二重フィルムを2組作成し、

左右2組のフィルムを一對のダイロール間を通して加熱圧着しながら内容液としてL-アスコルビン酸水溶液(濃度30%) 500mg/個を充填ポンプで圧入してカプセルを成形した。得られたカプセルを乾燥して軟カプセルが得られた。

(実施例2)

グルコマンナン	5部、
カラギナン	0.5部、
炭酸カルシウム	0.12部、
グリセリン	1部を70℃で30

分間混練して得られた組成物3部を水97部に溶解して得られた粘稠な水溶液を湿式キャスト法で製膜し15 μ 厚のフィルムを得た。このフィルムを用いて実施例1と同様にゼラチンフィルムとの二重構造の軟カプセル外皮を得た。内容液としてインスタントチキンスープ用の調味液2g/個を充填した軟カプセルを得た。この軟カプセル1個に90℃の熱湯150mlを加えて十分に攪拌したところ軟カプセルが崩壊し、チキンスープが得られた。

(実施例3)

ゼラチン100部、グリセリン30部、水10部を75℃で攪拌溶解し、真空ポンプで脱泡して得られた溶液をAとした。別に、グルコマンナン5部、カラギナン3.5部、グリセリン1.5部を70℃で混練して得られた本発明組成物3部を水97部に溶解して得られた水溶液をBとした。A60部とB40部を十分に攪り合わせてロータリー式連続軟カプセル自動充填機を用いて公知のロータリーダイス法によりアストリンゼンローション290mg/個を充填してNo. 5オーバルの軟カプセルを得た。使用時、針で軟カプセルを刺し、一回分の化粧水を取り出すことができた。

(効果)

本発明により、親水性の被充填物を水溶液の状態で軟カプセル化することが可能になり、軟カプセルの用途が一段と拡大した。

特許出願人 ユニコロイド株式会社
 代理人 弁理士 鈴木 定子

(19) Japanese Patent Office (JP)

(12) Official Gazette for Unexamined Patents (A)

(11) Kokai Patent No. Sho 63[1988]-164,858

(43) Kokai Date: July 8, 1988

(51) Int. Cl.⁴:
A 23 L 1/04

Identification Symbols:

Internal File No.:
6760-4B

Request for Examination: Requested

Number of Inventions: 1

(Total of 3 Pages)

(54) Outer Shell of Soft Capsule

(21) Application No. 61[1986]-309,109

(22) Filing Date: December 27, 1986

(72) Inventor: Masao Kubodera
203, Shibamachi, Kanezawa-ku, Yokohama-shi, Kanagawa-ken

(71) Applicant: Uni Colloid Co., Ltd.
7-8, Sakurayama 1 chome, Zushi-shi, Kanagawa-ken

(74) Agent: Sadako Suzuki

Specification

1. Title of the Invention

Outer Shell of Soft Capsule

2. Scope of Patent Claim

The outer shell of a soft capsule, the starting material of which is a natural polysaccharide-polyhydric alcohol composition obtained by uniformly mixing at least one natural polysaccharide of the following: carrageenan, alginic acid, alginic acid derivative, agar, locust bean gum, guar gum, tamarind seed polysaccharide, pectin, xanthan gum, glucomannan, chitin, pullulan, and cyclodextrin in a concentrated solution of at least one of the following: polyhydric alcohol, sugar alcohol, monosaccharide, disaccharide, and oligosaccharide in the presence or absence of an alkali.

3. Detailed Description of the Invention

[Industrial Field of Use]

The present invention pertains to the outer shell of a soft capsule that can be filled with a substance other than an oil.

[Prior Art]

Soft capsules are capsules wherein an oleaginous drug, etc., is introduced into a sheet made mainly of gelatin. These capsules have advantages in that the amount of liquid they hold is exact, their adhesive surface is perfectly sealed and therefore, there is no leakage and the contents are protected from outside air, in

turn making it possible to prevent oxidation and improve shelf life, and the productivity is high, etc.

Conventional soft capsules are made by mixing a gelatin starting material with glycerin or sorbitol, etc., to make an aqueous solution, gelling this solution and making the gel into a sheet, feeding two such sheets from a left and a right pair of die rolls while heating, continuously introducing and sealing the liquid between the two sheets, and drying.

[Problems to be Solved by the Invention]

As previously mentioned, soft capsules are excellent in terms of shelf life of their contents, their high productivity, etc., but because the gelatin is dissolved in water, their contents cannot be in the form of an aqueous solution and the only drug that can be introduced inside these capsules is one that can be dissolved in an oleaginous solvent. This restricts the use of soft capsules. Therefore, there is a need for an outer shell in soft capsule form that can even be filled with an aqueous solution.

[Means for Solving Problems]

The present invention solves the above-mentioned problems, its structure being characterized in that it uses as the starting material of the outer shell of the soft capsule a natural polysaccharide-polyhydric alcohol composition obtained by uniformly mixing at least one natural polysaccharide selected from carrageenan, alginic acid, alginic acid derivative, agar, locust bean gum, guar gum, tamarind seed polysaccharide, pectin, xanthan gum, glucomannan, chitin, pullulan, and cyclodextrin in a concentrated solution of at least one of the following: polyhydric

alcohol, sugar alcohol, monosaccharide, disaccharide, and oligosaccharide in the presence or absence of an alkali.

Polyhydric alcohols in the narrow sense of the word, such as propylene glycol, glycerin, etc., are given as polyhydric alcohols pertaining to the present invention. Sorbitol, mannitol, maltitol, xylitol, reduced starch saccharification product, etc., are given as sugar alcohols. Glucose, fructose, galactose, xylose, etc., are used as monosaccharides. Saccharose, maltose, lactose, etc., are used as disaccharides. The products of decomposition of starches such as sweet potato, white potato, and corn by enzymes, acids, etc., are used as oligosaccharides, and include disaccharides, trisaccharides, tetrasaccharides, pentasaccharides, hexasaccharides, etc.

Carrageenan, alginic acid, alginic acid derivative, agar, locust bean gum, guar gum, tamarind seed polysaccharide, pectin, xanthan gum, glucomannan, chitin, which is a type of mucopolysaccharide, pullulan, cyclodextrin, etc., can be widely used as natural polysaccharides.

Depending on the case, an alkali is preferably used concomitantly. The alkali should be an ordinary inorganic or organic alkaline substance, such as sodium hydroxide, potassium hydroxide, calcium hydroxide, magnesium hydroxide, barium hydroxide, sodium carbonate, potassium carbonate, calcium carbonate, ammonium carbonate, magnesium carbonate, sodium bicarbonate, ammonium bicarbonate, basic amino acid, amine, etc. When an alkali is added, strength and heat resistance will usually improve.

Furthermore, proteins can also be used concomitantly with the above-mentioned natural polysaccharides. Soy proteins, wheat protein, milk proteins, egg white, collagen, collagen decomposition products, microorganism proteins, etc., are given as the protein. Polypeptide, dipeptide, tripeptide, and amino acids are given as protein decomposition products. There is usually a tendency toward an increase in strength with a composition that is obtained by concomitant use of protein to replace part of the natural polysaccharide.

The present invention is characterized in that the natural polysaccharide is reacted in a concentrated solution of at least one of these polyhydric alcohols, sugar alcohols, monosaccharides, disaccharides and oligosaccharides. The concentrated solution is either the liquid form itself, or a slightly diluted liquid. The powder is made into an aqueous 30 to 90%, preferably 50 to 80%, more preferably 60 to 80%, solution and at least one of the above-mentioned polysaccharides is kneaded in this solution.

The temperature at which kneading is performed is 5 to 150°C, preferably 10 to 100°, more preferably 20 to 80°C. Even if kneading is performed at a low temperature, the reaction will be sufficient as long as the product is then heated when it is later dried, etc. In general, a composition with a delicate structure is obtained at a high temperature, while a composition whose mesh-like structure is coarse and brittle is obtained at a low temperature.

The mixture ratio of natural polysaccharide and at least one compound selected from: polyhydric alcohol, sugar alcohol, monosaccharide, disaccharide,

and oligosaccharide is 0.05 to 15 parts by weight, preferably 0.1 to 10 parts by weight, of these compounds to 1 part by weight of natural polysaccharide.

The composition obtained by kneading the above-mentioned starting materials is usually a slightly damp powder. When this is dissolved in water, it forms a sticky solution or paste with a solids content of 2 to 10% and can irreversibly congeal by being set aside at normal temperature, frozen, refrigerated or heated. Moreover, the congealed product that is obtained is preferred as the outer shell of a soft capsule because its properties, particularly strength, heat resistance and dissolution temperature in water, can be adjusted as needed by adjusting the starting materials that are used.

The following are given as embodiments of the outer shell of a soft capsule of the present invention:

(A) A substitute for a gelatin sheet that has been made by molding an aqueous solution of the composition pertaining to the present invention into a sheet with a thickness of 5 to 500 μ , preferably 10 to 50 μ ,

(B) A sheet that has been obtained by layering a gelatin sheet and a sheet of the composition pertaining to the present invention so that the sheet pertaining to the present invention is on the inside,

(C) A sheet that has been obtained by mixing a gelatin solution for soft capsules and a solution of the composition pertaining to the present invention.

Aqueous vitamin solutions of vitamin B₁, B₂, B₅, B₆, B₁₂, niacin, folic acid, vitamin C, etc., nutrients, such as saccharides, proteins, minerals, etc., encapsulated flavorings and seasonings, toiletries that are used in small amounts

at a time, etc., which have been difficult to use as a conventional oleaginous solution, are given as substances that are introduced into the soft capsule.

[Effects]

Natural polysaccharides have a complex structure with various reactive groups and side chains and therefore, apparently react in concentrated solutions in which many hydroxyl groups are present at high concentrations to form a complex matrix. When water is added to this, an even more complex three-dimensional structure is produced and a water-resistant, heat-resistant congealed product is irreversibly formed to produce a unique gel.

This type of gel is water-resistant and therefore, it can be preferably used as the outer shell of a soft capsule in which a substance such as a drug, a food product, or toiletry in the form of an aqueous solution is sealed and stored.

[Example 1]

One-hundred parts of gelatin, 30 parts of glycerin, and 60 parts of water were agitated and dissolved at 75°C and defoamed with a vacuum pump. A gelatin film with a thickness of 450 μm was obtained with a rotary-type continuous soft-capsule automatic filling device.

Five parts by weight of glucomannan, 2 parts by weight of carrageenan, and 1 part by weight of xanthan gum were separately kneaded with 1.5 parts of an 80% sucrose solution for 10 minutes at 80°C. Three parts by weight of the composition that was obtained were dissolved in 97 parts by weight of water and this aqueous solution was made into film by the wet casting method to obtain a film with a thickness of 25 μ . Two sets of double film in which the above-

mentioned gelatin film was layered onto this film were made. The two sets of films, a right and a left set, were passed through a pair of die rolls and heated and pressed while an aqueous L-ascorbic acid solution (concentration of 30%) was introduced under pressure by a filling pump to form capsules of 500 mg ascorbic acid/capsule.

[Example 2]

Glucomannan	5 parts
Carrageenan	0.5 part
Calcium carbonate	0.12 part
Glycerin	1 part

The above-mentioned components were kneaded for 30 minutes at 70°C and then 3 parts of the composition that was obtained were dissolved in 97 parts of water. The sticky aqueous solution that was obtained was made into film by the wet casting method to obtain a film with a thickness of 15 μ . The outer shell of a soft capsule having a two layered structure was obtained as in Example 1 using this film and a gelatin film. Soft capsules in which 2 g/capsule of flavoring liquid for instant chicken soup were introduced were obtained. When 150 ml of hot water at 90°C were added to one of these soft capsules and thoroughly agitated, the soft capsule broke to make chicken soup.

[Example 3]

One-hundred parts of gelatin, 30 parts of glycerin, and 10 parts of water were agitated and dissolved at 75°C. This was defoamed with a vacuum pump to obtain solution A. Five parts of glucomannan, 3.5 parts of carrageenan, and

1.5 parts of glycerin were separately kneaded at 70°C and 3 parts of the composition of the present invention that was obtained were dissolved in 97 parts of water to obtain aqueous solution B. Sixty parts of A and 40 parts of B were thoroughly kneaded and 290 mg of astringent lotion/capsule were introduced into No. 5 soft capsules by the conventional rotary die method using a rotary-type soft-capsule continuous automatic filling device. At the time of use, the soft capsule was pierced with a pin to obtain a dose of astringent lotion.

[Results]

By means of the present invention, it is possible to encapsulate hydrophilic contents in the form of an aqueous solution in a soft capsule, further increasing the use of soft capsules.

Applicant: Uni Colloid Co., Ltd.

Agent: Sadako Suzuki, Patent Attorney

InTransCo, Inc.

INTERNATIONAL TRANSLATION COMPANY

TRANSLATIONS FROM AND INTO ALL LANGUAGES PREPARED BY SPECIALISTS

P.O. BOX 239
LYNNFIELD, MA 01940
(781) 334-3123
FAX (781) 334-4445

CERTIFICATION OF TRANSLATION

Title(s) of Translated Document(s): JP 63-164,858

Original Language of Translated Document(s): Japanese

The undersigned declares that:

1. I am a professional translator representing InTransCo, Inc., with English as a native language and Japanese as an acquired language. With over twenty years of full-time translating experience in general, technical, chemical and related fields.
2. To the best of my knowledge and belief, the attached is a true, accurate and complete English translation of the above-referenced Japanese document(s).

Date: 2/22/03

Signature: Linda Hutchinson

Linda Hutchinson